



## SEAMASTER ICON HIGH GLOSS FINISH 4900

**3.27**  
Rev 09  
18/08/2025



<b>Description</b>	Seamaster Icon High Gloss Finish 4900 is a high gloss enamel finishing paint. It is formulated to provide fast drying with good levelling property enamel finish for exterior and interior use.
<b>Recommended Use</b>	It is recommended for both exterior and interior use on both wood and metal surfaces.
<b>Certification</b>	It complies with requirements under: <ul style="list-style-type: none"> <li>• Recognised as a Halal product by LPPOM (MUI) Indonesia</li> </ul>
<b>Physical Properties</b>	
Vehicle Type	Modified alkyd resin
Pigmentation	Mineral extenders, pigments and additives
Solvent	Seamaster S1230 thinner
Volume Solid	Approximately 55%
Drying Time at (27 ± 2°C & RH : 80 ± 5%)	Surface Dry ≤ 30 minutes Tack Free ≤ 2 hours Hard Dry ≤ 5 hours
Dry Film Thickness	18 ~ 22 microns per coat
Recoating Interval	≥ 5 hours
Theoretical Coverage	25 ~ 30 m <sup>2</sup> /litre ( <i>Actual coverage is dependent on substrate condition</i> )
Colours	Varies. Refer to colour card
Gloss at (60° head)	≥ 80%
Finish	High Gloss
Shelf Life	24 months (27 ± 2°C) in full sealed containers
Pot Life	N/A
Storage Condition	Air tight, store in dry and cool conditions
Packing	1 litre & 5 litres
Application Temperature	5°C to 40°C



**Application Method** By brush, roller or spray  
**Paint Preparation** Ready for use after thoroughly stirring. If necessary, thinning with not more than 5% of Seamaster S1230 thinner.  
**Cleaning Solvent** Seamaster S1230 thinner  
**Mixing Ratio** Single Pack

**Surface Preparation** **Wood Surface :**  
 The woodwork must be dry and free from dirt and other contaminants. Smoothen the surface by sanding and dust off before applying the paint system.  
**Metal Surface :**  
 Surface must be dry and free from efflorescence, dirt, grease, rust, and other contaminants before painting.  
**Previously Painted Surface :**  
 Surface to be painted must be thoroughly clean, dry and free from dirt, grease, loose material or flaking paint. All loose paint work must be scrapped off and defective areas should be sanded down and spot primed with suitable undercoat before painting.

### Recommended Coating System

#### a) For Woodwork

Sequence	Product Reference	No of Coat(s)	Dry Film Thickness
Undercoat	Seamaster White Undercoat 701	1	20 ~ 40 microns
Finish Coat	Seamaster Icon High Gloss Finish 4900	2	50 ~ 60 microns

#### b) For Metal

Sequence	Product Reference	No of Coat(s)	Dry Film Thickness
Primer	Seamaster Red Oxide 750	1	30 ~ 40 microns
Undercoat	Seamaster White Undercoat 701	1	20 ~ 40 microns
Finish Coat	Seamaster Icon High Gloss Finish 4900	2	50 ~ 60 microns

**Health and Safety** This product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Safety Data Sheet (SDS) are followed. SDS's are available upon request through your sales contract office, or via the Internet. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment.

### Product Liability

The Seller warrants the product to be free from manufacturing defects in material and workmanship. The Seller's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited at the Seller's option, to either replacement of products not conforming to this warranty or credit to the Buyer's account in the invoiced amount of the non-conforming products.

The Seller makes no other warranties concerning this product. No other warranties, either express or implied, or satisfactory, and as warranties or merchantability or fitness for a particular purpose, shall apply. In no event shall the Seller be liable for consequential or incidental damages. Any recommendations or suggestion relating to the use of the products made by the Seller, whether in its technical limitation, or in response to specific inquiry, or otherwise, is based on data believed to be reliable, however, the products and information are intended for Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that the Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use or extrapolation of data may cause unsatisfactory results.