



SEAMASTER SUPERGLO HIGH GLOSS FINISH 6600

3.5(ii)
Rev 07
18/08/2025



Description	Seamaster Superglo High Gloss Finish 6600 is an excellent gloss enamel finishing paint. It is specially formulated to provide fast drying for both exterior and interior application. It can be used on wood and metal substrates to form a durable and tough paint film.
Recommended Use	It is recommended for exterior and interior for both wood and metal surfaces.
Certification	It complies with requirements under: <ul style="list-style-type: none"> • Recognised as a Halal product by LPPOM (MUI) Indonesia
Physical Properties	
Vehicle Type	Modified alkyd resin enamel
Pigmentation	Weather resistant pigments
Solvent	S1230 Thinner
Volume Solid	Approximately 40%
Drying Time at (27 ± 2°C & RH : 80 ± 5%)	Touch Dry ≤ 1 hour Hard Dry ≤ 3 hours
Dry Film Thickness	25 ~ 35 microns per coat
Recoating Interval	≥ 3 hours
Theoretical Coverage	11 ~ 16 m ² /litre (<i>Actual coverage is dependent on substrate condition</i>)
Colours	Varies. As per colour card
Gloss at (60° head)	≥ 80%
Finish	High Gloss
Shelf Life	36 months (27 ± 2°C) in full sealed containers
Pot Life	N/A
Storage Condition	Air tight, store in dry and cool conditions
Packing	1 litre & 5 litres
Application Temperature	5°C to 40°C



Application Method By brush, roller or spray
Paint Preparation Ready for use after thoroughly stirring. If necessary, thinning with not more than 5% of S1230 Thinner.
Mixing Ratio N/A

Surface Preparation Ensure that the surface is clean and dry. Metal surface should be free from mill scales and rust and appropriately primed. Remove unstable film from previously painted surfaces.

Recommended Coating System

a) For Woodwork

Sequence	Product Reference	No of Coat(s)	Dry Film Thickness
Primer	Seamaster Red Lead Primer 739(S)	1	20 ~ 30 microns
Undercoat	Seamaster Synlac White Undercoat 7000N	1	30 ~ 40 microns
Finish Coat	Seamaster Superglo High Gloss Finish 6600	2	60 ~ 70 microns

b) For Steel & Iron

Sequence	Product Reference	No of Coat(s)	Dry Film Thickness
Primer	Seamaster Red Oxide 750	1	30 ~ 40 microns
Undercoat	Seamaster Micaceous Iron Oxide (MIOX) 1300	1	30 ~ 40 microns
Finish Coat	Seamaster Superglo High Gloss Finish 6600	2	60 ~ 70 microns

c) For Aluminium & Galvanised Iron

Sequence	Product Reference	No of Coat(s)	Dry Film Thickness
Etching Primer	Seamaster Etching Primer 9500	1	15 ~ 20 microns
Undercoat	Seamaster Micaceous Iron Oxide (MIOX) 1300	1	30 ~ 40 microns
Finish Coat	Seamaster Superglo High Gloss Finish 6600	2	60 ~ 70 microns

Health and Safety This product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Safety Data Sheet (SDS) are followed. SDS's are available upon request through your sales contract office, or via the Internet. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment.



Product Liability

The Seller warrants the product to be free from manufacturing defects in material and workmanship. The Seller's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited at the Seller's option, to either replacement of products not conforming to this warranty or credit to the Buyer's account in the invoiced amount of the non-conforming products.

The Seller makes no other warranties concerning this product. No other warranties, either express or implied, or satisfactory, and as warranties or merchantability or fitness for a particular purpose, shall apply. In no event shall the Seller be liable for consequential or incidental damages. Any recommendations or suggestion relating to the use of the products made by the Seller, whether in its technical limitation, or in response to specific inquiry, or otherwise, is based on data believed to be reliable, however, the products and information are intended for Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that the Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use or extrapolation of data may cause unsatisfactory results.