



# SEAMASTER FLOOR DRESSING POLYURETHANE VARNISH COATING CLEAR (GLOSS / MATT) 2992 / 2994

**7.5**  
Rev 06  
03/04/2023



<b>Description</b>	Seamaster Floor Dressing Polyurethane Varnish Coating Clear (Gloss / Matt) 2992 / 2994 is a one-pack polyurethane varnish, specially formulated for parquet floor. As it is one-pack polyurethane, it is easy to apply giving a good levelling and high gloss finish. This material also give a good properties to all wood surfaces as it is resistant to most household material like alcohol, sauce, lipstick etc. It also excellent resistance to hot and cold water and anti-termites.
<b>Recommended Use</b>	As a finish for protection and decoration of exterior and interior wood surfaces such as parquet floors, cane and wood furniture.
<b>Surface Preparation</b>	<p><b>New Surface :</b> Surfaces should be smooth without areas of fur, evenly pre-sanded with no coarser than 150 grit paper. The surface must be free from contaminating waxes, oils and silicones.</p> <p><b>Previously Painted Surface :</b> Surface to be painted must be thoroughly clean, dry and free from dirt, grease and loose or flaking coating. All paint works must be scrapped off and defective areas should be sanded down and spot primed with appropriate filler before painting.</p>
<b>Certification</b>	<p>It complies with requirements under:</p> <ul style="list-style-type: none"> <li>Recognised as a Halal product by LPPOM (MUI) Indonesia</li> </ul>
<b>Physical Properties</b>	
Vehicle Type	Single pack polyurethane
Pigmentation	Weathering resistant, special pigments
Solvent	Seamaster S1230 thinner
Density (kg/litre)	0.90 ~ 1.00
Volume Solid	Approximately 50%
Drying Time at (27 ± 2°C & RH : 80 ± 5%)	Touch Dry ≤ 1 hour Hard Dry ≤ 4 hours
Dry Film Thickness	25 ~ 30 microns per coat
Recoating Interval	≥ 3 hours to overnight
Theoretical Coverage	16 ~ 20 m <sup>2</sup> /litre ( <i>Actual coverage is dependent on substrate condition</i> )
Colours	Translucent
Gloss at (60° head)	2992 – 90 ± 5% 2994 – 25 ± 5%
Finish	2992 – Glossy 2994 – Matt
Shelf Life	12 months (27 ± 2°C) in full sealed containers
Pot Life	N/A
Storage Condition	Air tight, store in dry and cool conditions
Packing	1 litre & 5 litres
Application Temperature	5°C to 40°C
<b>Application Method</b>	By brush, roller or spray
Paint Preparation	Ready for use after thoroughly stirring. If necessary, thinning with not more than 5% of mineral turpentine or Seamaster S1230 thinner may be added.
Cleaning Solvent	Seamaster S1230 thinner
Mixing Ratio	Single Pack



## Health and Safety

This product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Safety Data Sheet (SDS) are followed. SDS's are available upon request through your sales contract office, or via the Internet. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment.

## Product Liability

The Seller warrants the product to be free from manufacturing defects in material and workmanship. The Seller's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited at the Seller's option, to either replacement of products not conforming to this warranty or credit to the Buyer's account in the invoiced amount of the non-conforming products.

The Seller makes no other warranties concerning this product. No other warranties, either express or implied, or satisfactory, and as warranties or merchantability or fitness for a particular purpose, shall apply. In no event shall the Seller be liable for consequential or incidental damages. Any recommendations or suggestion relating to the use of the products made by the Seller, whether in its technical limitation, or in response to specific inquiry, or otherwise, is based on data believed to be reliable, however, the products and information are intended for Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that the Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use or extrapolation of data may cause unsatisfactory results.